



Youth Tipped V-Neck Raglan Windshirt



Front



Back

YST62

- 100% polyester
- Jersey lining with mesh insets at gussets for added breathability
- Rib-knit v-neck collar
- Tipping on the collar and at gussets

Care Instructions:
 Machine wash cold, gentle cycle with like colors
 Use mild detergent, remove immediately
 Do not allow to lay on itself when wet
 Do not Bleach

Finished Measurements in Inches					
Size	XS	S	M	L	XL
Width	33	36	39	42	45
Length	21 1/2	22 1/2	23 1/2	24 1/2	25 1/2
Sleeve	24	26	28	31	34

Chest width measured 1" below armhole. Body length measured from center back to hem.
 Sleeve length measured from CB to hem. Collar measured by circumference.

Colors	
	Black/True Red
	Black/White
	Forest Green/White
	Maroon/White
	Purple/White
	True Navy/Gold
	True Navy/White
	True Red/White
	True Royal/White

Color Chart				
Colors	Black	True Red	White	Forest Green
Textile PMS	No Match	No Match	No Match	No Match
General PMS	Process Black	194C	No Match	No Match
Colors	Maroon	Purple	True Navy	Gold
Textile PMS	No Match	No Match	No Match	No Match
General PMS	No Match	No Match	No Match	137C
Colors	True Royal			
Textile PMS	No Match			
General PMS	No Match			

Please Note:
 Colors shown are approximate and for reference only. For closest match see PMS colors, or for exact match, returnable samples and grommited samples are available.

Dri Mesh® Short Sleeve T-Shirt

Sport-Tek
By Port Authority

Dri-mesh Screen Printing Recommendation

Factors during printing:

Heat Absorption: Polyester will naturally attract more heat than a natural fiber such as cotton. When high heat is applied to polyester; like other types of polymers (such as plastics) it will reach a melting point.

Garment Color: The garment color is a factor to consider when printing. Darker colors such as Black, Dk. Green, Maroon, Navy, Red & Steel will experience higher shrinkage. It is especially important to test these colors before printing the entire run. Black will always have the highest shrinkage rate.

Outside Temperature: If you are printing in a warmer climate, we recommend you take into account the outside temperature. This will increase the temperature during printing as well as when the garment passes through the dryer.

Printing Steps:

Test Sample: It's recommended to run a test garment (in a dark color) before printing the entire run of garments. This will allow you to gauge the temperature of the imprint as it passes through the dryer.
Note: Black will always attract & retain the highest amount of heat during drying.

Ink Type: Dri-mesh fabric is stretchy due to the construction, so it is recommended to use a plastisol additive or an ink specifically used for full synthetic fabrics. The printed surface will be less likely to crack and the imprint will stretch with the fabric.

Ink Application: We recommend a 2-stroke application of ink per color process. Flash in between colors for no more than 10 – 15 seconds. Keep in mind; the heavier the ink coverage applied the greater chance of puckering around the printed area. Excessive ink coverage will attract more heat during the drying process.

Printing Surface: If your print surface is metal/aluminum and you have been printing all day; the surface will get hot. Factors like outside temperature and ventilation through the print facility may also make the print surface hotter. If this is a factor you contend with, we recommend running a fan on the opposite side of the flash board.

Dryer Temperature: We recommend the dryer temperature to be set between 290 – 300 degrees Fahrenheit depending on the outside temperature in your area. Remember the polyester will attract more heat as it passes through the dryer.

Print Cure Temperature: If the dryer temperature is set between 290 – 300 degrees Fahrenheit, the imprinted surface will cure between 305 – 320 degrees. Keep in mind, the darker the garment color & imprint, the more heat the garment will attract. Adjust your dryer accordingly.

Drying Time: We recommend the fabric be exposed to the dryer for no more than 75 seconds.

Heat Gun: To gauge the heat of the garment and imprint area as it passes through the dryer; a heat gun will assist greatly in gauging the temperature. Exttech Instrumental sells a gun starting at \$100.

Dri-mesh Screen Printing Recommendation

Q & A:

Q: How do I know the garment has been flashed too long?

A: If you are performing a 2+ color process, you may notice a shadow or an overlapping of the ink with the next color application. This is an indication the garment is shrinking under the direct heat of the flash area. Shorten the garments exposure to no more than 10 – 15 seconds and let it sit for at least 45 seconds before the next application.

Q: How do I know my drying temperature is too high?

A: You may notice puckering around the imprint area as well as along the seams of the garment. Using a heat gun is the best way to make sure the garment is not coming out of the dryer too hot.

Q: How do I know the ink application is too heavy or too light?

A: You may notice on your test sample puckering around the imprint area if the application is too heavy. Again, the ink will attract more heat than the garment itself. You want to apply enough ink to prevent the garment color from showing through the imprint.

Q: I only have 1 dryer to print cotton & polyester garments together:

A: Screening on cotton may require a higher temperature for curing. If you have 1 dryer to do both, set aside the polyester garments until you have some free space to run once the dryer has cooled to the correct temperature. Make sure the staging area is clean and free of contaminants until ready.